



TYPICAL DATA SHEET | ISSUE DATE | FEB-16

GRADE	WWW.TPCO.IR
GPPS1540	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745- 354/TEL:+984134282612

GPPS1540 is an easy flowing crystal polystyrene designed for extrusion or injection applications. It improves extruder output and thermoforming cycle time when mixed with a high impact polystyrene such as HIPS7240. It is particularly suitable for glossy-layer coextrusion.

Applications:

packaging articles, petri dishes, office equipments, pen barrels, crisper boxes for refrigerators, cups, food containers gloss layer coextrusion. anionic styrene butadiene copolymer dilution.

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX(200°C-5KG)	g/10min	ASTM D-1238	11
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
VICAT SOFTENING POINT (50 °C/hr 1kg)	°C	ASTM D-1525	91
ROCKWELL HARDNESS	--	ASTM D-1525	L SCALE/ 70
TENSILE STRENGTH AT BREAK	MPA	ASTM D-638	42
ELONGATION AT BREAK	%	ASTM D-638	2
TENSILE MODULUS	MPA	ASTM D-638	3100



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurul Tower Şişli, İstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



*All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (Standard Sales Specifications)

Density and shrinkage of this grade are approximately around 1.04 kg/lit & (0.4-0.7)%(ASTM D-955) respectively.

All test are carried out at 23°C , unless otherwise stated.

If in grade reference the fourth digit is "1"(1541) , indicates an external lubricants is included.

If the injection molding products quality is affected by moisture, granules of GPPS could be dried at 70°C for 2-4 hours.



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurol Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
BEAD SIZE	MM	SUNPOR 7 2 5 (MIN 90% BY WT)	1-1.8
K-VALUE	--	SUNPOR 7.2.4	52-57
PENTANE CONTENT	WT%	SUNPOR 7.2.2	MIN 5.2
MOISTURE CONTENT	WT%	SUNPOR 7.2.3	MAX 1
RESIDUAL MONOMER	PPM	SUNPOR 7.2.1	MAX 1000

* FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurol Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



TYPICAL DATA SHEET | ISSUE DATE | FEB-16

GRADE	WWW.TPCO.IR
GPPS1540	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745- 354/TEL:+984134282612

GPPS1540 is an easy flowing crystal polystyrene designed for extrusion or injection applications. It improves extruder output and thermoforming cycle time when mixed with a high impact polystyrene such as HIPS7240. It is particularly suitable for glossy-layer coextrusion.

Applications:

packaging articles, petri dishes, office equipments, pen barrels, crisper boxes for refrigerators, cups, food containers gloss layer coextrusion. anionic styrene butadiene copolymer dilution.

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX(200°C-5KG)	g/10min	ASTM D-1238	11
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
VICAT SOFTENING POINT (50 °C/hr 1kg)	°C	ASTM D-1525	91
ROCKWELL HARDNESS	--	ASTM D-1525	L SCALE/ 70
TENSILE STRENGTH AT BREAK	MPA	ASTM D-638	42
ELONGATION AT BREAK	%	ASTM D-638	2
TENSILE MODULUS	MPA	ASTM D-638	3100



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurul Tower Şişli, İstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM