



TYPICAL DATA SHEET | ISSUE DATE | FEB-15

GRADE	WWW.TPCO.IR
HS221	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745- 354/TEL:+984134282612

HS221 , is one of the TPC Performance expandable polystyrene products range. It is a free flowing expandable polystyrene grade,consisting of spherical polystyrene beads containing pentane as the expansion agent. Expandable polystyrene (EPS) is normally expanded to achieve the low densities required for final step expansion.The typical density of this grade is around 22 kg/m³,but other densities are possible depending on applications and equipments.

HS221 is specially high strength formulated to achieve low density foam without lumps during preexpansion.

This grade is not fire retardent ,so it is not suitable for bulding applications.

Applications:

Medium Density Block

Low- and medium-density foam blocks made from HS 221 are used as thermal insulation boards for construction applications without special requirements concerning flame resistance or as packaging blanks.

Packaging and storage:

HS221 is shipped in octabins (height 176 cm) on wooden pallets (115cm x 115 cm), containing 1000 kg netof material.

The octabins are not weather- or water-proof and must therefore not be exposed to outdoor conditions.

In order to obtain the desired properties of HS221, the raw material should be stored below 20 °C and be processed within 1 month.



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurul Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



Processing:

Preexpansion:

With discontinuously operating, state-of-the-art preexpanders HS221 can be preex-panded to densities of approx. 22 kg/m³. Lower densities can be achieved by double preexpansion or in optimized machines.

HS221 has been treated with an antistatic agent to prevent a buildup of electro-static charge during transport.

Intermediate aging:

Intermediate aging should be between 10 and 48 hours.

Moulding:

HS221 can be processed in industry standard moulding machines within a relatively wide range of steaming settings.

If a regenerative agent is added care has to be taken that the density of the regenerative agent equals the preexpansion density as closely as possible to prevent a segregation during production.

Typical Properties

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
BEAD SIZE	MM	SUNPOR 7.2.5 (MIN 90% BY WT)	(1-1.8)(>90%wt)
K-VALUE	--	SUNPOR 7.2.4	55
PENTANE CONTENT	WT%	SUNPOR 7.2.2	5.2%
EXPANDED DENSITY	KG/M ³	SUNPOR 7.2.6	14-30
RESIDUAL MONOMER	PPM	SUNPOR 7.2.1	500



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurul Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
BEAD SIZE	MM	SUNPOR 7 2 5 (MIN 90% BY WT)	1-1.8
K-VALUE	--	SUNPOR 7.2.4	52-57
PENTANE CONTENT	WT%	SUNPOR 7.2.2	MIN 5.2
MOISTURE CONTENT	WT%	SUNPOR 7.2.3	MAX 1
RESIDUAL MONOMER	PPM	SUNPOR 7.2.1	MAX 1000

* FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS.



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurol Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM



TYPICAL DATA SHEET | ISSUE DATE | FEB-15

GRADE	WWW.TPCO.IR
HS221	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745- 354/TEL:+984134282612

HS221 , is one of the TPC Performance expandable polystyrene products range. It is a free flowing expandable polystyrene grade,consisting of spherical polystyrene beads containing pentane as the expansion agent.

Expandable polystyrene (EPS) is normally expanded to achieve the low densities required for final step expansion.The typical density of this grade is around 22 kg/m³,but other densities are possible depending on applications and equipments.

HS221 is specially high strength formulated to achieve low density foam without lumps during preexpansion.

This grade is not fire retardent ,so it is not suitable for bulding applications.

Applications:

Medium Density Block

Low- and medium-density foam blocks made from HS 221 are used as thermal insulation boards for construction applications without special requirements concerning flame resistance or as packaging blanks.

Packaging and storage:

HS221 is shipped in octabins (height 176 cm) on wooden pallets (115cm x 115 cm), containing 1000 kg netof material.

The octabins are not weather- or water-proof and must therefore not be exposed to outdoor conditions.

In order to obtain the desired properties of HS221, the raw material should be stored below 20 °C and be processed within 1 month.



Adress İzzetpaşa Mahallesi, Yeni yol Caddesi, No: 3,
Kat 3 Ofis No. 303Nurul Tower Şişli,Vstanbul /Turkey



Tel +90 2129 827 486
Fax +90 8505 223 403
Mob +90 534 271 38 22



Website www.RGMPETROKIMYA.com
Email Commercial@rgmpetrokimya.com
WhatsApp & Telegram @RGM

RGM